



TECHNICAL DATA SHEET – NOVOREZ® 353

Revised: 9/2017

DESCRIPTION

NovoRez 353 is a 100% solids, multi-functional polymer coating system formulated to resist aggressive chemical immersion. The coating combines micro fillers and epoxy novolac resin with a special “stress-relieving” additive to provide maximum durability and superior compatibility.

TYPICAL APPLICATION

BASECOAT	NovoRez 353BC @ 15 mils
TOPCOAT	NovoRez 353TC @ 15 mils

PERFORMANCE DATA

COMPRESSIVE STRENGTH (ASTM C-579)	20,000 psi
TENSILE STRENGTH (ASTM D-638)	4,000 psi
FLEXURAL STRENGTH (ASTM C-580)	4,300 psi
BOND STRENGTH (ASTM D-4541)	425 psi
OPERATING TEMPERATURE, MAXIMUM, DRY: WET:	185°F Dependent on chemical exposure
VOC	0.0 lb/gal; 0.0 gm/L
VOLUME SOLIDS	100%

BENEFITS

- Maximum chemical resistance to inorganic acids such as phosphoric, hydrochloric acids
- Superior flexibility compared to vinyl ester, polyester or conventional novolac coatings
- Longer service life than thin mil epoxy phenolics
- 100% solids, zero VOC formulation
- Applies at 15 mils per coat without sagging, running or dripping

RECOMMENDED USES

- Internal vessel linings
- Acid frac tanks
- Chemical transport trucks
- Structural steel in acidic conditions

GENERIC DESCRIPTION

Polysulfide-Modified Epoxy Novolac

PACKAGING / COLORS

- | | |
|----------------------------------|-----------------------|
| 3-Gallon Units (sold separately) | <u>STANDARD COLOR</u> |
| • NovoRez 353BC Basecoat | Sand |
| • NovoRez 353TC Topcoat | Medium Gray |

MIX RATIO: 2R : 1H

COVERAGE: 100 ft² / gallon @ 15 mils

NOVOREZ® 353
STEEL COATING, ACID RESISTANT TANK LINING

STORAGE & INSTALLATION

STORAGE ENVIRONMENT	Dry area, 65–80°F
APPLICATION TEMPERATURE, AMBIENT	50–95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5°F above dew point
SHELF LIFE	1 year
POT LIFE, @ 77°F	30 minutes
SET TIME, @ 77°F	4–6 hours
FULL SERVICE, @ 77°F	7 days

SURFACE TEMPERATURE

NOVOREZ®353 BASECOAT	60-69°F	70-89°F	90°F
RECOAT (MIN)	6-8 hours	4-5 hours	2-3 hours
RECOAT (MAX)	20-24 hours	12-16 hours	6-8 hours

CONSIDERATIONS & LIMITATIONS

1. Confirm product performance in specific chemical environment prior to use.
2. Prepare substrate according to “Surface Preparation” portion of this document.
3. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
4. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
5. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

STEEL: For immersion service, “White Metal” abrasive blast with an anchor profile of 4–5 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, “Near White” SP-10-63 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

Use the following instructions for both the NovoRez 353BC (Basecoat) and NovoRez 353TC (Topcoat):

NOTE: *NovoRez 353BC Basecoat promotes adhesion while NovoRez 353TC Topcoat’s quick curing time allows fast return to service. These products are formulated for use together as a system, and should not be used individually.*

1. Component A Resin should be premixed prior to using due to possible pigment settling that may occur during transportation and storage.
2. **OPTIONAL STEP:** If product will be spray applied, sprayability can be improved by mixing 5–10% (by total volume) toluene into Component A Resin prior to adding Component B Hardener.
3. Pour Component B Hardener into the Component A Resin pail and mix with a mechanical jiffy-type mixer operated at low speed until a uniform blend is attained. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.
NOTE: *Do not overmix. Product will become increasingly viscous if overmixed.*
NOTE: *Do not turn the pail upside down and allow to drain onto substrate.*
4. Apply by brush, roller or spray.
NOTE: *Do not exceed recommended application thickness; doing so will result in stress build-up within the coating, resulting in cracking and delamination.*
5. After the basecoat has become slightly tack free (within approximately 4 hours @ 70°F), prepare and apply a coat of NovoRez 353TC Topcoat resin/hardener mixture following the instructions outlined in Steps 1–4.
NOTE: *If the basecoat becomes glossy and/or hard to the touch, a light sanding followed by a wipe with a 50:50 mixture of water and isopropanol will be necessary before applying the topcoat. Allow the solvent to flash before applying topcoat.*

2R:1H / DOC NR353-TDS
© Copyright 2017. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW’s sole obligation and Buyer’s exclusive remedy in connection with the products shall be limited, at ITW’s option, to either replacement of products not conforming to this warranty or credit to Buyer’s account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW in writing within five days of Buyer’s discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer’s failure to notify ITW of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW cannot guarantee that color will conform to sample, if provided.