



## TECHNICAL DATA SHEET – THIOKOL® 2235M

Revised: 09/2017

### DESCRIPTION

Thiokol 2235M is a high performance, non-sag, certified per NSF/ANSI Standard 61, chemical resistant elastomeric joint sealant. Due to its high polysulfide polymer content, it is resistant to many chemicals, shrinkage, aging, thermal stress and the effects of outdoor exposure.

### TYPICAL APPLICATION

PRIMER	Thiokol 5050 Primer @ 3-5 mils (concrete) Thiokol 5050 Primer @ 2-3 mils (steel)
BACKER ROD	Customer supplied
SEALANT	Thiokol 2235M
OPTIONS	Thiokol CR Chemical Resistant Joint Sealant System adds PolySpec 196BA and PolySpec 196SL Thiokol DC Dual Containment Joint Sealant System adds Thiokol RLP 2378+ and Engineering Fabric

### PERFORMANCE DATA

TENSILE STRENGTH (ASTM D - 412)	150-200 psi
ELONGATION (ASTM D - 412)	500-550%
HARDNESS, SHORE A (ASTM D - 2240)	25-30
JOINT MOVEMENT	±25%
VOC	0.0 lb/gal; 0.0 gm/L
VOLUME SOLIDS	100%
VOC EMISSIONS (TVOC, CDPH V1.1-2010)	<0.5 mg/m <sup>2</sup>

### APPROVALS

- Certified per NSF/ANSI Standard 61
- MIL TT-S-00227, Type II, non-sag
- ASTM C-920, Type M, Grade NS, Class 25, Use NT, M, G, A and O
- Meets IAQ emission requirements for California's Sec. 01350 and Appendix B

### BENEFITS

- Retains elasticity even as concrete moves; maintains flexibility over time
- Resists mild acids, alkalis and petroleum products
- Resists effects of sunlight, rain, snow, ozone, aging, shrinkage and cyclic temperature changes, even after years of service
- Contains no volatile solvents

### RECOMMENDED USES

Concrete expansion joints:

- Water treatment & storage facilities
- Bridges
- Roadways
- Warehouse floors
- Secondary containment dike walls & floors
- Tank chine seals
- Concrete panels

**GENERIC DESCRIPTION:** Polysulfide Sealant

**STANDARD COLORS:** Gray

**PACKAGING:** 1.5-Gallon Unit

**MIX RATIO:** 12R: 1H

### COVERAGE:

JOINT SIZE	COVERAGE PER GALLON
1/2" W x 1/4" D	154 linear ft
1/2" W x 1/2" D	77 linear ft
3/4" W x 1/2" D	51 linear ft
1" W x 1/2" D	38 linear ft
1" W x 3/4" D	25 linear ft

*Coverages are theoretical only.*

**THIOKOL® 2235M**  
INDUSTRIAL POLYSULFIDE JOINT SEALANT, NON SAG

**STORAGE & INSTALLATION**

STORAGE ENVIRONMENT	Dry area, 65-80°F
APPLICATION TEMPERATURE, AMBIENT	50-95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5° above dew point
SHELF LIFE	18 month
POT LIFE, @ 77°F	1 hour
TACK FREE, @ 77°F	6 hours
FULL CURE, @ 77°F	7 days

*Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.*

**CONSIDERATIONS & LIMITATIONS**

1. Do not thin with solvents unless advised to do so by ITW Engineered Polymers.
2. Confirm product performance in specific chemical environment prior to use.
3. Prepare substrate according to "Surface Preparation" portion of this document.
4. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
5. For industrial/commercial use. Installation by trained personnel only.

**SURFACE PREPARATION**

**CONCRETE:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.

**STEEL:** For immersion service, "White Metal" abrasive blast with an anchor profile of 2-4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

**Refer to PolySpec Surface Preparation Guidelines for more details.**

**INSTALLATION STEPS**

**BASE SYSTEM: Thiokol 2235M HP High Performance Joint Sealant System**

1. Prime surface with Thiokol 5050 Primer. See data sheet for application details.
2. Install a backer rod into the joint; the backer rod should be compressed 25%. When a backer rod is not feasible, bond breaker tape is acceptable.  
**NOTE: Ideally, the joint depth should be one half the joint width.**
3. Add Component B to Component A and mix at slow speed (250-300 RPM) with a 1/2" drill 2 part sealant mixing paddle until material is completely blended. Scrape down sides of container and mixing paddle periodically during mixing; thorough blending of the components is essential for maximum performance of the sealant.

**NOTE: Typical mixing time is 3-5 minutes.**

4. Thiokol 2235M is supplied in a non-sag consistency that will gun easily with conventional caulking equipment. Fill joint completely. The best installation is done with a bulk caulk gun such as an Albion model # DL-45-T13 or suitable equal.

**NOTE: Proper width to depth ratios must be maintained.**

5. Immediately after application, dry tool the sealant using a spatula. Use light pressure to ensure positive and complete contact of the sealant to the joint surfaces. Non-sag sealants should be tooled with a suitable sealant spatula with a rounded tip similar to the 258 series by Albion to provide a concave finish thereby creating the desired hour-glass configuration. Spatulas should be slightly wider than the width of the expansion joint.

**NOTE: Care must be taken to avoid contamination of open joints. Blocking may be required.**

**OPTIONAL UPGRADE: Thiokol 2235M CR Chemical Resistant Joint Sealant System**

1. Perform steps 1-5 of Thiokol 2235M HP System, above.
2. Apply PolySpec 196BA Bonding Agent. Must be left open for chemical reaction for 16 hours. See data sheet for application details.
3. Using masking or duct tape, mask off edges of the expansion joint, leaving 1/4" to 1/2" of the concrete exposed.
4. Apply two coats of PolySpec 196SL. See data sheet for application details.  
**NOTE: The second coat can be applied 20 to 30 minutes after the first coat.**
5. Pull masking tape 10-15 minutes after the second coat is applied.

**OPTIONAL UPGRADE: Thiokol 2235M DC Dual Containment Joint Sealant System**

1. Perform steps 1-5 of Thiokol 2235M HP System, above.
2. Abrasive blast concrete surface 4" on each side of the expansion joint.
3. Using duct tape, mask off the concrete 3" on both sides of the expansion joint.
4. Prime the prepared concrete surface with Thiokol 5050 Primer.
5. Prepare and apply one 20 mil coat of Thiokol RLP 2378+ by roller. See data sheet for application details.
6. Immediately lay engineering fabric into coating. Press it in with a dry roller.
7. Saturate the fabric with an additional 20 mil coat of Thiokol RLP 2378+.
8. Before the coating cures, pull all tape.

For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

C-12R:1H / DOC 2235M-TDS  
PolySpec is a ® Registered Trademark of ITW Engineered Polymers  
Thiokol is a ® Registered Trademark of ITW Engineered Polymers  
© Copyright 2017 PolySpec All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**ITW makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by ITW, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW cannot guarantee that color will conform to sample, if provided.