



## TECHNICAL DATA SHEET – TUFFREZ® 201CC

Revised: 2/2017

### DESCRIPTION

TuffRez 201CC, a two-component, 100% solids, crystal clear epoxy topcoat for coating and sealing concrete floors, offers improved UV stability compared to conventional epoxy coatings. Mixed with PolySpec Color Packs, this durable material cures to a smooth, glossy color surface finish or, with the addition of aggregate, a non-skid texture. Color quartz or flakes can also be used with TuffRez 201CC to produce a seamless, decorative surface.

### TYPICAL APPLICATION

PRIMER	PolySpec Epoxy Primer @ 5-7 mils
BASECOAT	TuffRez 201CC @ 15-20 mils
TOPCOAT	TuffRez 201CC @ 15-20 mils
OPTIONS	Non-Skid Grit Integral Cove Base Flexible Waterproofing & Crack-Bridging Membrane Decorative Quartz (see DL-2 System) Flakes (see DF System) Anti-Microbial Formulation Upgrade (TuffRez 201CC-AM)

### PERFORMANCE DATA

COMPRESSIVE STRENGTH (ASTM C-579)	9,000 psi
TENSILE STRENGTH (ASTM D - 638)	1,700 psi
FLEXURAL STRENGTH (ASTM C-580)	4,000 psi
HARDNESS, SHORE D (ASTM D - 2240)	85-90
BOND STRENGTH (ASTM D - 4541)	425 psi
ABRASION RESISTANCE (ASTM D - 4060)	80 mg
OPERATING TEMPERATURE, MAXIMUM, DRY:	130°F
WET:	Dependent on chemical exposure
VOLUME SOLIDS	100%
VOC	0 g/L

### BENEFITS

- Improved clarity and UV stability over conventional epoxy coatings, and at a lower cost than urethane topcoats
- Versatile design possibilities
  - Solid colors using easy-mix color packs
  - Multi-color quartz and flake finishes
  - Various surface finishes available
- Provides excellent fill for decorative quartz broadcast, creating effect of much thicker application with fewer and less costly steps
- Seamless, monolithic flooring
- Withstands mechanical damage from foot traffic and rubber wheel devices
- Resists many acids, alkalis and salts

### RECOMMENDED USES

- Warehousing & manufacturing facilities
- Chemical processing plants
- Laboratories, hospitals, healthcare facilities
- Stadiums & other entertainment venues
- Educational & institutional facilities
- Cafeterias, kitchens, storefronts, aisles
- Bathrooms, showers

**GENERIC DESCRIPTION:** Epoxy

**STANDARD COLORS:** Clear  
Solid Colors: See "Color Packs, Epoxy"  
Decorative Broadcast: Quartz or Flake

**PACKAGING:** 3-Gallon Unit

**MIX RATIO:** 2R: 1H

**COVERAGE:** 100 ft<sup>2</sup> / gallon @ 16 mils

**TUFFREZ® 201CC**  
EPOXY COATING, UV STABLE

**STORAGE & INSTALLATION**

STORAGE ENVIRONMENT	Dry area, 65-80°F
APPLICATION TEMPERATURE, AMBIENT	50-95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5° above dew point
SHELF LIFE	1 year
POT LIFE, @ 77°F	20 minutes
FOOT TRAFFIC, @ 77°F	8-10 hours
SERVICE, @ 77°F	Light: 24 hours / Full: 48-72 hours
RECOAT WINDOW	Minimum: 8 hours, Maximum: 72 hours

**CONSIDERATIONS & LIMITATIONS**

1. This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the flooring.
2. Do not use partial units. Prolonged exposure of product in containers to air may cause loss of clarity.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by ITW Engineered Polymers.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

**SURFACE PREPARATION**

**CONCRETE:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.
- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.

**Refer to PolySpec Surface Preparation Guidelines for more details.**

**INSTALLATION STEPS**

1. Prime surface with a PolySpec Primer for epoxies on concrete surfaces. See data sheet for application details
2. **OPTIONAL STEP:** If integral cove base is desired, install cap strip at the top of the base and divider strip at doorways and other places as required.
3. Component A Resin should be premixed prior to using due to possible additive separation.
4. **OPTIONAL STEP:** For color version, add pre-mixed Epoxy Color Pack(s) to Component A. Refer to "Color Pack, Epoxy" data sheet for mix ratio and mixing instructions.
5. Pour Component B Hardener into the Component A Resin pail and mix for a minimum of two minutes, using a mechanical jiffy-type mixer operated at low speed. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.  
**NOTE: Do not turn the pail upside down and allow to drain onto substrate.**
6. **OPTIONAL STEP:** For cove base, mix fumed silica thixotrope into resin/hardener mixture until desired consistency is achieved. Trowel into place.
7. Apply resin/hardener mixture by roller or squeegee and back-roll. Move quickly and empty contents of pail onto surface as soon as possible to provide maximum working time. Material left in the pail will generate heat and have a reduced pot life.  
**NOTE: Back-roll lightly if necessary. DO NOT OVER ROLL. Too much rolling may introduce small air bubbles into system.**
8. **OPTIONAL STEP:** When applied as a non-skid coating, broadcast clean, dry 20/40-mesh sand or aluminum oxide aggregate into wet resin. Allow to dry. A full broadcast to refusal will produce the most consistent and durable system. Brush off excess grit before applying second coat.  
**NOTE: Do not broadcast aggregate into the prime coat.**
9. After the first coat has become slightly tack free (within approximately 10 hours of cure @ 70°F), apply a second coat of resin/hardener mixture, following the application procedure outlined in Step 7.  
**NOTE: If the coating has not been recoated within 48 hours, a light sanding followed by a wipe with a 50:50 mixture of water and isopropanol may be necessary. Allow the solvent to flash before applying coating.**
10. ITW Engineered Polymers offers a diverse line of epoxy and CRU topcoats for enhanced resistance to UV exposure, chemicals, abrasive wear, and other performance requirements. Please refer to ITW Engineered Polymers' online catalog at [www.polyspec.com](http://www.polyspec.com), or contact ITW Engineered Polymers or an Authorized Representative.
11. Always wear gloves when using this product.

© Copyright 2017. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**ITW makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by ITW, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW cannot guarantee that color will conform to sample, if provided.