



## TECHNICAL DATA SHEET – THIOKOL® FEC® 2233

Revised: 2/2017

### DESCRIPTION

FEC 2233 is a 100% solids, two-component flexible epoxy coating for concrete and steel surfaces. Its unique formulation incorporates a polysulfide polymer into the backbone of the epoxy chain that prevents the “age hardening” of conventional epoxy coatings.

### TYPICAL APPLICATION

|           |  |
|-----------|--|
| PRIMER    | PolySpec 100EX @ 5–7 mils (concrete) or American Safety MS11CZLT Primer @ 4–6 mils (steel) |
| BASE COAT | FEC 2233 @ 16–20 mils (horizontal); @ 7–8 mils (vertical)                                  |
| TOP COAT  | FEC 2233 @ 16–20 mils (horizontal); @ 7–8 mils (vertical)                                  |
| OPTIONS   | Non Skid Grit  |

### PERFORMANCE DATA

|   |                                |
|---|--------------------------------|
| COMPRESSIVE STRENGTH (ASTM C - 579)     | 18,000 psi                     |
| TENSILE STRENGTH (ASTM D - 638)         | 2,500 psi                      |
| FLEXURAL STRENGTH (ASTM C - 580)        | 4,300 psi                      |
| HARDNESS, SHORE D (ASTM D - 2240)       | 65-75                          |
| BOND STRENGTH (ASTM D - 4541)           | 425 psi                        |
| OPERATING TEMPERATURE, MAXIMUM,<br>DRY: | 180°F                          |
| WET:                                    | Dependent on chemical exposure |
| ABRASION RESISTANCE (ASTM D - 4060)     | 70 mg                          |
| ELONGATION, % AT BREAK                  | 30-40                          |
| C - TEAR, LBS/IN (ASTM D - 1004)        | 305+                           |
| IMPACT STRENGTH, IN/LBS (ASTM D - 4226) | 20+                            |
| VOC                                     | 0.00 lb/gal; 0.0 gm/L          |
| VOLUME SOLIDS                           | 100%                           |

### BENEFITS

- Maintains toughness over time
- Excellent resistance to chipping
- Excellent penetration and bond strength
- Chemical resistance to dilute acids, caustics and petroleum solvents
- Low odor, 100% solids epoxy
- Increased thermal shock resistance
- High abrasion resistance

### RECOMMENDED USES

- Secondary containment
- Drum storage
- Vehicle service bays
- Truck unloading areas
- Covered parking decks
- Chemical processing areas
- Manufacturing facilities
- Warehouse floors
- Aisles
- Mechanical rooms

**GENERIC DESCRIPTION:** Polysulfide-Modified Epoxy

**STANDARD COLORS:** Medium Gray

**MIX RATIO:** 2R : 1H

**PACKAGING:** 3-Gallon Unit

### COVERAGE:

80 ft<sup>2</sup> / gallon @ 20 mils  
100 ft<sup>2</sup> / gallon @ 16 mils  
200 ft<sup>2</sup> / gallon @ 8 mils

**THIOKOL® FEC® 2233**  
CONCRETE & STEEL COATING, FLEXIBLE EPOXY

**STORAGE & INSTALLATION**

|                                    |                            |
|------------------------------------|----------------------------|
| STORAGE ENVIRONMENT                | Dry area, 65-80°F          |
| APPLICATION TEMPERATURE, AMBIENT   | 50-95°F                    |
| APPLICATION TEMPERATURE, SUBSTRATE | Minimum 5° above dew point |
| SHELF LIFE                         | 1 year                     |
| POT LIFE, @ 77°F                   | 30 minutes                 |
| FOOT TRAFFIC, @ 77°F               | 16 hours                   |
| FULL SERVICE, @ 77°F               | 48 hours                   |

**SURFACE TEMPERATURE**

|              | 60 - 69°F     | 70 - 89°F     | 90°F        |
|--------------|---------------|---------------|-------------|
| RECOAT (MIN) | 18 - 24 hours | 4 - 8 hours   | 2 - 3 hours |
| RECOAT (MAX) | 60 - 72 hours | 48 - 60 hours | 24 hours    |

**CONSIDERATIONS & LIMITATIONS**

1. Due to viscosity, some roller lines may appear when applying to horizontal surfaces.
2. ITW Engineered Polymers recommends the use of a slip resistant grit with this product.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by PolySpec.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document.
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

**SURFACE PREPARATION**

**CONCRETE:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.

- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.

**STEEL:** For immersion service, "White Metal" abrasive blast with an anchor profile of 2-4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

**Refer to PolySpec Surface Preparation Guidelines for more details**

**INSTALLATION STEPS**

1. Prime surface with appropriate primer. See data sheet for application details.
2. Component A Resin should be premixed prior to using due to possible pigment settling that may occur during transportation and storage.
3. Pour Component B Hardener into the Component A Resin pail and mix well with a mechanical jiffy-type mixer operated at low speed. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.  
**NOTE: Do not turn the pail upside down and allow to drain onto substrate.**
4. Apply by roller or squeegee and back-roll. Move quickly and empty contents of pail onto surface as soon as possible to provide maximum working time. Material left in the pail will generate heat and have a reduced pot life.
5. OPTIONAL STEP: When applied as a non-skid coating, broadcast clean, dry 20/40-mesh sand or aluminum oxide aggregate into wet resin. Allow to dry. A full broadcast to refusal will produce the most consistent and durable system. Brush off excess grit before applying second coat.  
**NOTE: Do not broadcast aggregate into the prime coat.**
6. After the first coat has become slightly tack free (within approximately 10 hours of cure @70°F), apply an additional coat of resin/hardener mixture according to Step 4.  
**NOTE: If the coating has not been recoated within 48 hours, a light sanding followed by a wipe with a 50:50 mixture of water and isopropanol may be necessary. Allow the solvent to flash before applying coating.**
7. Always wear gloves when using this product.

2R:1H / DOC FEC2233-TDS

© Copyright 2017. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**ITW makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by ITW, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW cannot guarantee that color will conform to sample, if provided.