



## TECHNICAL DATA SHEET – NOVOREZ® 360+

Revised: 2/2017

### DESCRIPTION

NovoRez 360+ is a 100% solids, two component epoxy novolac coating suited for highly aggressive chemical environments.

### TYPICAL APPLICATION

|          |  |
|----------|--|
| PRIMER   | PolySpec 100EX @ 5–7 mils  |
| BASECOAT | Concrete: NovoRez 351 @ 15-20 mils<br>Steel: NovoRez 353 BC @ 15-20 mils |
| TOPCOAT  | NovoRez 360+ @ 15-20 mils  |
| OPTIONS  | Non-Skid Grit @ 0.50 lbs/ft <sup>2</sup>                                 |

### PERFORMANCE DATA

|   |                                |
|---|--------------------------------|
| COMPRESSIVE STRENGTH (ASTM C - 579)                 | 22,000 psi                     |
| TENSILE STRENGTH (ASTM D - 638)                     | 4,000 psi                      |
| ELONGATION (ASTM D - 638)                           | <1%                            |
| FLEXURAL STRENGTH (ASTM C - 580)                    | 4,300 psi                      |
| BOND STRENGTH (ASTM D - 4541)<br>(CONCRETE FAILURE) | 425 psi                        |
| ABRASION RESISTANCE (ASTM D - 4060)                 | 70 mg                          |
| OPERATING TEMPERATURE, MAXIMUM,<br>DRY:             | 300°F                          |
| WET:  | Dependent on chemical exposure |
| VOC   | 0.0 lb/gal; 0.0 gm/L           |
| VOLUME SOLIDS                                       | 100%                           |

### BENEFITS

- Resists wide range of the most aggressive solvents and chemicals including perchloroethylene, tetrahydrofuran, pyridine, organic and inorganic acids, alkalies and salts
- 100% solids, zero VOC formulation
- No heating, baking or post curing required to achieve chemical resistance
- Lower viscosity than standard novolacs

### RECOMMENDED USES

- Chemical process floors
- Secondary containment
- Pump pedestals
- Aircraft paint stripping areas
- Trenches & sumps

### GENERIC DESCRIPTION:

Epoxy Novolac

### STANDARD COLORS:

Medium Gray

### PACKAGING:

3-Gallon Unit

### MIX RATIO:

3.46R : 1H

### COVERAGE:

80 ft<sup>2</sup> / gallon @ 20 mils

**NOVOREZ® 360+**  
CONCRETE AND STEEL COATING, SOLVENT RESISTANT

**STORAGE & INSTALLATION**

|                                    |                             |
|------------------------------------|-----------------------------|
| STORAGE ENVIRONMENT                | Dry area, 65-80 °F          |
| APPLICATION TEMPERATURE, AMBIENT   | 50-95°F                     |
| APPLICATION TEMPERATURE, SUBSTRATE | Minimum 5°F above dew point |
| SHELF LIFE                         | 1 year                      |
| POT LIFE, @ 77°F                   | 25 minutes                  |
| FOOT TRAFFIC, @ 77°F               | 16 hours                    |
| FULL SERVICE, @ 77°F               | 7 days                      |
| RECOAT WINDOW                      | -                           |

**SURFACE TEMPERATURE**

|              | 60-69°F     | 70-89°F     | 90°F      |
|--------------|-------------|-------------|-----------|
| RECOAT (MIN) | 6-8 hours   | 4-5 hours   | 2-3 hours |
| RECOAT (MAX) | 20-24 hours | 12-16 hours | 6-8 hours |

**CONSIDERATIONS & LIMITATIONS**

1. ITW Engineered Polymers recommends the addition of non-skid grit for floors, secondary containment and process areas subjected to foot traffic and forklift traffic. For heavy traffic areas, trenches and sumps, ITW Engineered Polymers recommends NovoRez 360+ as a topcoat over the PermaRez 348 system.
2. For best results, work area should be humidity and temperature controlled.
3. Protect area from direct sunlight during application and from sudden temperature changes within 24 hours of application.
4. Do not thin with solvents unless advised to do so by ITW Engineered Polymers.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document.
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

**SURFACE PREPARATION**

**CONCRETE:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.
- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.

**STEEL:** For immersion service, "White Metal" abrasive blast with an anchor profile of 2-4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

**INSTALLATION STEPS**

1. Prime surface with PolySpec Primer. See data sheet for application details.
2. Apply one Basecoat of NovoRez 351. See data sheet for application details.  
**NOTE: NovoRez 351 is used as the basecoat because it has a longer recoat window than the NovoRez 360+.**

3. Component A Resin should be premixed prior to using due to possible pigment settling that may occur during transportation and storage.

4. Pour Component B Hardener into the Component A Resin pail and mix with a mechanical jiffy-type mixer operated at low speed until a uniform blend is attained. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.

**NOTE: Do not overmix. Product will become increasingly viscous if overmixed.**

**NOTE: Do not turn the pail upside down and allow to drain onto substrate.**

5. Apply by squeegee and back-roll. Move quickly and empty contents of pail onto surface as soon as possible to provide maximum working time. Material left in the pail will generate heat and have a reduced pot life.

**NOTE: Do not exceed recommended application thickness; doing so will result in stress build-up within the coating, resulting in cracking and delamination.**

6. Follow application with a spiked plastic roller to remove entrapped air.

**7. OPTIONAL STEP: NON-SKID COATING**

When applied as a non-skid coating, broadcast clean, dry 20/40-mesh sand or aluminum oxide aggregate into wet resin. Allow coating to cure. A full broadcast to refusal will produce the most consistent and durable system. Brush off excess grit before applying second coat.

**NOTE: Broadcast grit into the basecoat of NovoRez 351. Do not broadcast into the prime coat.**

After the first coat has become slightly tack free (within approximately 4 hours @ 70°F), apply an additional coat of resin/hardener mixture according to Step 4.

**NOTE: If more than 24 hours have elapsed or the basecoat becomes glossy and/or hard to the touch, a light sanding followed by a wipe with a 50:50 mixture of water and isopropanol will be necessary before applying the second coat. Allow the solvent to flash before applying coating.**

3.46R:1H / DOC NR360+-TDS

NovoRez and PolySpec are® Registered Trademarks of ITW Engineered Polymers.

© Copyright 2017 ITW Engineered Polymers. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW Engineered Polymers' sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Engineered Polymers' option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Engineered Polymers in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Engineered Polymers of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**ITW Engineered Polymers makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by ITW Engineered Polymers, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Engineered Polymers cannot guarantee that color will conform to sample, if provided.