



TECHNICAL DATA SHEET – POLYSPEC® 300EX

Revised: 2/2017

DESCRIPTION

PolySpec 300EX is a penetrating, moisture tolerant, two-component epoxy primer used to prime concrete surfaces for high performance applications. It is commonly utilized as part of a complete flooring system and is also suited for use with epoxy novolac lining systems.

TYPICAL APPLICATION

PRIMER	PolySpec 300EX Primer @ 175-200 ft ² /gallon
OVERCOAT	Flooring or Lining System from PolySpec

PERFORMANCE DATA

BOND STRENGTH (ASTM D - 4541)	450 psi
VOC	0.45 lb/gal; 54 gm/L
VOLUME SOLIDS	94%

STORAGE & INSTALLATION

STORAGE ENVIRONMENT	Dry area, 65-80°F
APPLICATION TEMPERATURE, AMBIENT	40-95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5°F above dew point
SHELF LIFE	1 year
POT LIFE, @ 77°F	60 minutes
SET TIME @ 77°F	4-6 hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

BENEFITS

- Low viscosity formulation penetrates and seals concrete pores
- Provides superior adhesion to substrate and higher tensile and flexural strengths when compared to conventional polyamide primers
- Cures at ambient temperatures down to 40°F
- Resistant to amine blush, even when cured at low temperatures and high humidity
- Requires zero induction time

RECOMMENDED USES

- Concrete primer, as part of a complete TuffRez® flooring system
- Concrete primer, as part of a complete epoxy novolac lining system

GENERIC DESCRIPTION:

Primer

STANDARD COLORS:

Amber

MIX RATIO:

1.33R: 1H

PACKAGING:

1.5-Gallon Unit

COVERAGE:

175-200 ft²/gallon

May vary depending on concrete porosity

POLYSPEC® 300EX
EPOXY PERFORMANCE PRIMER FOR CONCRETE

CONSIDERATIONS & LIMITATIONS

1. ITW Engineered Polymers does not recommend that grit be broadcast or otherwise introduced into PolySpec 300EX Primer. If enhanced slip resistance is desired, the flooring systems' body coat or topcoat may be specified to serve this function.
2. This product is not designed to provide complete hide and color coverage. If complete hide is required, use additional TuffRez topcoats.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by ITW Engineered Polymers.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document.
7. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
8. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

CONCRETE: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.
- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

1. Component A Resin should be premixed prior to using due to possible additive separation.
2. Pour Component B Hardener into the Component A Resin pail and mix for a minimum of two minutes, using a mechanical jiffy-type mixer operated at low speed. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.
3. Apply resin/hardener mixture by roller or squeegee, followed by a backroll with a short nap roller. Move quickly and empty contents of pail onto surface as soon as possible to provide maximum working time. Material left in the pail will generate heat and have a reduced pot life.
4. **OPTIONAL STEP:** Once primer has become tacky to the touch, a second primer coat may be applied.
NOTE: *Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*
NOTE: *Broadcasting grit into PolySpec 300EX Primer is not recommended.*
5. Once primer has become tacky to the touch, proceed to installation of a PolySpec flooring or lining system; refer to technical data sheet for installation instructions.
NOTE: *Pay special attention not to contaminate surface when working on primer that has not cured to a tack-free surface.*
NOTE: *Primed surfaces should be recoated within 48 hours. For longer waiting periods, wipe with xylene until surface becomes tacky. If surface remains hard, abrasive sanding followed by a wipe with a 50:50 mixture of water and isopropanol will be necessary. Allow the solvent to flash before applying coating.*

1.33R:1H / DOC PS300EX-TDS

PolySpec is a © Registered Trademark of ITW Engineered Polymers.

© Copyright 2017 ITW Engineered Polymers. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW Engineered Polymers' sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Engineered Polymers' option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Engineered Polymers in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Engineered Polymers of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW Engineered Polymers makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Engineered Polymers be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW Engineered Polymers, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Engineered Polymers cannot guarantee that color will conform to sample, if provided.