



TECHNICAL DATA SHEET – THIOKOL® 5050

Revised: 3/2017

DESCRIPTION

Thiokol® 5050 primer is a low viscosity primer used to prime concrete and steel surfaces for Thiokol polysulfide sealants.

TYPICAL APPLICATION

PRIMER	Thiokol® 5050 Primer @ 700-800 linear ft/unit (concrete) – 2-3 mils (steel)
SEALANT	Thiokol® polysulfide sealant system

PERFORMANCE DATA

VOC	0.0 gm/L
VOLUME SOLIDS	65%

STORAGE & INSTALLATION

STORAGE ENVIRONMENT	Dry area, 65-80°F
APPLICATION TEMPERATURE, AMBIENT	40-95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5° above dew point
SHELF LIFE	1 year
POT LIFE, @ 77°F	3 hours
RECOAT TIME FOR CONCRETE, @ 77°F	min 2 hours / max 36 hours
RECOAT TIME FOR STEEL, @ 77°F	min 4 hours / max 36 hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

BENEFITS

- Low viscosity formulation penetrates and seals concrete pores
- Easy 1:1 volume mixing
- Easy to apply
- Fast recoat time

RECOMMENDED USES

- Concrete and steel primer as part of a complete Thiokol® Sealant System

GENERIC DESCRIPTION:

Epoxy Primer

STANDARD COLORS:

Clear Amber

PACKAGING:

0.25-Gallon Unit

MIX RATIO:

1R : 1H

COVERAGE:

½" – 960 linear ft/unit

1" – 480 linear ft/unit

700–800 linear ft/unit (concrete)

1100-1300 linear ft/unit (steel)

May vary depending on concrete porosity

THIOKOL® 5050
EPOXY PRIMER FOR POLYSULFIDE SEALANTS

CONSIDERATIONS & LIMITATIONS

1. Do not thin with solvents unless advised to do so by ITW Engineered Polymers.
2. Confirm product performance in specific chemical environment prior to use.
3. Prepare substrate according to "Surface Preparation" portion of this document.
4. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
5. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

CONCRETE: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surfacelayers.
- Concrete should have a minimum surfacetensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.
- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.

STEEL: For immersion service, "White Metal" abrasive blast with an anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details

INSTALLATION STEPS

1. Component A Resin should be premixed prior to using due to possible additive separation.
2. Pour Component B Hardener into the Component A Resin pail and mix by hand for a minimum of two minutes. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.
3. Thiokol 5050 Primer can be applied by brush.
4. Allow primer to cure within recommended recoat time before proceeding to application of Thiokol sealant.
5. For best results, clean tools and equipment with PolySpec[®] All Purpose Cleaner, a nonflammable and nonnon-evaporating cleaner. Always wear gloves when using this product.

Premixed / DOC 5050-TDS

Thiokol is a [®] Registered Trademark of ITW Engineered Polymers
© Copyright 2017 PolySpec All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your ITW Engineered Polymers representative for current technical data and instructions.

ITW Engineered Polymers warrants its products to be free from defects in material and workmanship. ITW's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW cannot guarantee that color will conform to sample, if provided.