



TECHNICAL DATA SHEET – FNEC® 2515

Revised: 6/2019

DESCRIPTION

THIOKOL FNEC 2515 is a 100% solids, two-component, flexible novolac epoxy coating suited for use on concrete and steel substrates. It provides protection from chemical attack and environmental degradation in primary and secondary containment applications.

TYPICAL APPLICATION

PRIMER	PolySpec 100EX @ 5–7 mils (concrete) or American Safety MS-11CZ LT Primer @ 4–6 mils (steel) (steel surfaces may not require a primer)
BASE COAT	FNEC 2515 @ 16–20 mils
TOP COAT	FNEC 2515 @ 16–20 mils

PERFORMANCE DATA

TENSILE STRENGTH (ASTM C - 638)	700 psi
HARDNESS, SHORE D (ASTM C - 2240)	35-40
ELONGATION	75%
OPERATING TEMPERATURE, MAXIMUM	160°F
DRY:	Dependent on chemical exposure
WET:	
VOC	0.00 lb/gal; 0.00 gm/L
VOLUME SOLIDS	100%

BENEFITS

- 100% solids, zero VOC formulation
- Excellent resistance to petroleum and urea ammonium nitrate (UAN) products
- Easy application - 1:1 mix ratio, sprays in two 16-20 mil coats
- Flexibility beyond conventional tank linings
- High impact resistance

RECOMMENDED USES

- Above ground tanks
- Underground fuel storage tanks
- Tank bottoms
- Rail car linings
- Secondary containment

GENERIC DESCRIPTION: Polysulfide-Modified Novolac Epoxy

STANDARD COLORS: Light Gray, White
Contrasting colors should be used for basecoat and topcoat to ensure complete coverage.

PACKAGING: 10-Gallon Unit

MIX RATIO: 1R : 1H

COVERAGE: 100 ft² / gallon @ 16 mils

FNEC® 2515

CONCRETE & STEEL COATING, FLEXIBLE NOVOLAC EPOXY

STORAGE & INSTALLATION

STORAGE ENVIRONMENT	Dry area, 65-80°F
APPLICATION TEMPERATURE, AMBIENT	50-95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5° above dew point
MAXIMUM SERVICE TEMPERATURE	160°F
SHELF LIFE	2 year
POT LIFE, @ 77°F	20 minutes
FOOT TRAFFIC, @ 77°F	16 hours
FULL SERVICE, @ 77°F	7 days

SURFACE TEMPERATURE

	65°F	75°F	90°F
RECOAT (MIN)	32 hours	16 hours	6 hours
RECOAT (MAX)	4 days	72 hours	48 hours

CONSIDERATIONS & LIMITATIONS

1. Due to viscosity, some roller lines may appear when applying to horizontal surfaces.
2. This product will amber/yellow with exposure to UV.
3. Do not thin with solvents unless advised to do so by ITW Polymers Sealants North America, Inc.
4. Confirm product performance in specific chemical environment prior to use.
5. Prepare substrate according to "Surface Preparation" portion of this document.
6. Always use protective clothing, gloves and goggles during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
7. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

CONCRETE: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- New concrete should be cured a minimum of 28 days.
- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- Moisture vapor emission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.
- All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.
- Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.

STEEL: For immersion service, "White Metal" abrasive blast with an anchor profile of 2-4 mills in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

1. Prime surface with PolySpec 100EX or American Safety MS-11CZ LT Primer @ 4-6 mils. See data sheet for application details.
2. Component A Resin should be premixed prior to using due to possible pigment settling that may occur during transportation and storage.
3. Prepare and apply a 16-20 mil coat of FNEC 2515 according to one of the methods outlined below:

Plural Component Heated Spray Equipment (recommended)

Plural mixing is the preferred method of application. A 1:1 ratio airless spray pump, such as a Graco XP70, should be used. Component A Resin and Component B Hardener should be separately premixed prior to using due to possible pigment settling that may occur during transportation and storage. Component A should be heated to 110-120° F. Component B should be heated to 110-120° F. The hose should be heated to 120° F Run Component A through a 3/8" heated line to the mixing manifold. Run Component B through a 3/8" heated line to the mixing manifold. A 12" (24 turn), 3/8 stainless steel static mixer should be installed coming off the mix manifold. From the static mixer install a 3/8" 25 foot fluid hose. From the fluid hose install an additional 12" (24 turn), 3/8" stainless steel static mixer. Using a reducer attach a 1/4" "Whip" hose approximately 10 feet in length. The whip hose should attach directly to the Spray Gun.

NOTE: Fluid lines should be wrapped with foam and protected with a scuff jacket. Remove the filters from the gun and the pump. Adjust the fluid pressure of Component A and Component B to 2400-3000 psi. Use a 0.021-0.029 tip. Immediately flush lines & static mixers, if spraying is stopped for more than three minutes. Heated material will begin to gel within 10 minutes time at 120°F. Repairs may be done by brush, roller, or spray.

Batch Mixing for Roller, Squeegee, Brush' Pour Component B Hardener into Component A Resin pail. Mix well for 2-3 minutes using a mechanical jiffy-type mixer operated at low speed until a consistent color is attained. Scrape container sides to ensure a proper blend. Apply by roller, squeegee or brush.

NOTE: Work very quickly due to the product's short pot life

4. Always wear gloves when using this product.

1R:1H / DOC FNEC2515-TDS

© Copyright 2019 ITW Polymers Sealants North America, Inc. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your ITW Polymers Sealants North America, Inc. representative for current technical data and instructions.

ITW Polymers Sealants North America, Inc. warrants its products to be free from defects in material and workmanship. ITW Polymers Sealants North America, Inc.'s sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Polymers Sealants North America, Inc.'s option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Polymers Sealants North America, Inc. in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Polymers Sealants North America, Inc. of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW Polymers Sealants North America, Inc. makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Polymers Sealants North America, Inc. be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW Polymers Sealants North America, Inc. whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Polymers Sealants North America, Inc. can not guarantee that color will conform to sample, if provided.